

SGG ENVISION

SGG NEBULA (SKN 454)

HIGH SPECTRAL SELECTIVITY (LIGHT-HEAT RATIO)

OFFERING ADVANCED OCCUPANT THERMAL COMFORT



SGG NEBULA (SKN 454)

SGG Nebula is an advanced Solar and Thermal insulation glass for energy efficient glazing. Manufactured by deposition of specialized metallic oxides, SGG Envision is created using a magnetically enhanced Nano - technology based cathodic sputtering process, and is the most energy efficient glass in its class.

FEATURES

SGG NEBULA is engineered exclusively for buildings that need a seamless balance of natural lighting and Solar control.

- **High spectral selectivity**
(Ratio of Light Transmission to Solar Heat gain coefficient)
- **High thermal insulation**
- **Enhanced Daylighting**
- **Advanced Solar Control**

THICKNESSES

- Standard thicknesses of 4mm, 5mm, 6mm are available
- 8mm available on special request.

PROCESSING

To obtain its performance and aesthetics, SGG Nebula must be

- Tempered /Heat Strengthened
- Assembled into an IGU

SGG Nebula can also be used as

- Laminated units
- Bent units

APPLICATIONS

- Structural glazing
- Façade glazing
- Bolted systems
- Curtain wall glazing
- Fenestration applications.
- Best suited for buildings having extensive glazing requirements.

SUSTAINABILITY

As the world leader in glass manufacturing for the construction market, Saint-Gobain worldwide is committed to provide innovative solutions to two key challenges of the future:

- **Environmental protection**
- **Energy savings**
- **SGG Nebula conforms to:**



SKN 454, an energy efficient glass on a tinted base comes with **Active Glare Reduction**, filtering out glare like none other. So that you get to enjoy enhanced visual comfort, higher productivity and a whole world of wellbeing.

PRODUCT PERFORMANCE

SGG NEBULA (SKN 454)

6 mm Coated Glass (Coating Face 2) – 12 mm Air Gap – 6 mm Clear Glass

LIGHT FACTORS		
TRANSMISSION (%)	REFLECTION (%)	
	EXTERNAL	INTERNAL
42	14	22

(EN)	ENERGY FACTORS		(EN)
SOLAR FACTOR	SHADING CO-EFFICIENT	U-VALUE	
SHGC / SF	SC	(W/Sq.m K)	
0.24	0.27	1.5	

(NFRC)	ENERGY FACTORS		(NFRC)
SOLAR FACTOR	SHADING CO-EFFICIENT	U-VALUE	
SHGC / SF	SC	(W/Sq.m K)	
0.23	0.26	1.5	

Thermal transmittance factors are determined by EN 673
Solar and Luminous factors are determined by EN 410

Solar Characteristics as per NFRC 200/300-2010
Thermal Transmittance as per NFRC 100 -2010.

SGG NEBULA (SKN 454)

SGG NEBULA UNDER SUNNY CONDITIONS



SGG NEBULA UNDER OVERCAST CONDITIONS

