

# SGG ENVISION

## SKN 776

HIGH SPECTRAL SELECTIVITY (LIGHT-HEAT RATIO)

OFFERING ADVANCED OCCUPANT THERMAL COMFORT



# SGG ENVISION (SKN 776)

SGG Envision SKN 776 is an advanced Solar and Thermal insulation glass for energy efficient glazing. Manufactured by deposition of specialized metallic oxides, SGG Envision is created using a magnetically enhanced Nano - technology based cathodic sputtering process, and is the most energy efficient glass in its class.

## FEATURES

SGG Envision SKN 776 is engineered exclusively for buildings that need a seamless balance of natural lighting and Solar control.

- **High spectral selectivity**  
(Ratio of Light Transmission to Solar Heat gain coefficient)
- **High thermal insulation**
- **Optimum Daylighting**
- **Advanced Solar Control**
- **Blue appearance**
- **Low reflections**



## THICKNESSES

- Standard thicknesses of 4mm, 5mm, 6mm are available
- 8mm available on special request.



## PROCESSING

To obtain its performance and aesthetics, SGG Envision SKN 776 must be

- Tempered /Heat Strengthened
- Assembled into an IGU

SGG Envision SKN 776 can also be used as

- Laminated units
- Bent units



## APPLICATIONS

- Structural glazing
- Façade glazing
- Bolted systems
- Curtain wall glazing
- Fenestration applications.
- Best suited for buildings having extensive glazing requirements.



## SUSTAINABILITY

As the world leader in glass manufacturing for the construction market, Saint-Gobain worldwide is committed to provide innovative solutions to two key challenges of the future:

- **Environmental protection**
- **Energy savings**
- **SKN 776 conforms to:**



**AGR**  
Active Glare Reduction

SKN 776, an energy efficient glass on a tinted base comes with **Active Glare Reduction**, filtering out glare like none other. So that you get to enjoy enhanced visual comfort, higher productivity and a whole world of wellbeing.

## PRODUCT PERFORMANCE

### SGG Envision SKN 776

6 mm Coated Glass (Coating Face 2) – 12 mm Air Gap – 6 mm Clear Glass

LIGHT FACTORS		
TRANSMISSION (%)	REFLECTION (%)	
	EXTERNAL	INTERNAL
44	8	13

(EN)	ENERGY FACTORS		(EN)
SOLAR FACTOR	SHADING CO-EFFICIENT	U-VALUE	
SHGC / SF	SC	(W/Sq.m K)	
0.26	0.30	1.5	

(NFRC)	ENERGY FACTORS		(NFRC)
SOLAR FACTOR	SHADING CO-EFFICIENT	U-VALUE	
SHGC / SF	SC	(W/Sq.m K)	
0.25	0.29	1.6	

Thermal transmittance factors are determined by EN 673  
Solar and Luminous factors are determined by EN 410

Solar Characteristics as per NFRC 200/300-2010  
Thermal Transmittance as per NFRC 100 -2010.

# SGG ENVISION SKN 776

SGG Envision SKN 776 UNDER SUNNY CONDITIONS



SGG Envision SKN 776 UNDER OVERCAST CONDITIONS

